

WESTERN ASSAYERS
 Engineers, Metallurgists and Chemists
 224 South Spring St.
 Los Angeles, Calif.
 NORMAN W. PARLEE, Mining Engineer

PHONE MUTUAL 2806
 Special Low Rates to Prospectors

ASSAY CERTIFICATE

Los Angeles, Calif., Dec. 21st 1935

We hereby Certify that the samples described below, received from
W. R. Maxwell, Room 45, City Hall assay as follows:

Owner's Mark and Sample	GOLD		SILVER		TOTAL VALUE PER TON	PERCENTAGE OF		
	OZS. PER TON	VALUE PER TON	OZS. PER TON	VALUE PER TON		COPPER	LEAD	ZINC
<u>483-Falcon #1</u>	<u>.005</u>	<u>.20</u>	<u>104.34</u>	<u>80.35</u>	<u>80.55</u>	<u>94.10</u>		

104.34
90
939.00

GOLD @ \$ 36 PER OZ. LEAD @ \$ ____ C.
 SILVER @ \$ 77 PER OZ. COPPER @ \$ ____ C. CHARGES 75[¢] Paid
Norman W. Parlee
 ASSAYER

@ 90

Our dependable assays will bring you back — We check, double check and guarantee our work.

THE EISENHOWER LABORATORIES
 316-322 South San Pedro Street
 Los Angeles 13, California

ASSAY CERTIFICATE

PHONE MADISON 2-8328

Los Angeles, Calif. Sept. 5/62 19

I hereby Certify that the samples described below, received from

W. R. Maxwell

assay as follows:

Owner's Mark and Sample	GOLD		SILVER		TOTAL VALUE PER TON	PERCENTAGE OF		
	OZS. PER TON	VALUE PER TON	OZS. PER TON	VALUE PER TON		COPPER	LEAD	ZINC
Outcrop of float			1078.40	\$1197.02	\$ 1197.02			

GOLD @ \$ _____ PER OZ.
 SILVER @ \$ 1.11 PER OZ.
 LEAD @ _____ C.
 COPPER @ _____ C.

CHARGER _____

ASSAYER

Established 1916

THE EISENHAUER LABORATORIES
 316-322 South San Pedro Street
 Los Angeles 13, California

ASSAY CERTIFICATE

PHONE MADRON 2-9328

I hereby Certify that the samples described below, received from Los Angeles, Calif. Feb. 27/63
W. R. Maxwell

assay as follows:

Owner's Mark and Sample	GOLD		SILVER		TOTAL VALUE PER TON	PERCENTAGE OF		
	OZS. PER TON	VALUE PER TON	OZS. PER TON	VALUE PER TON		COPPER	LEAD	ZINC
Taken from stope off of 65 ft. entrance of Falcon Mine			6395.1	\$7671.12				

GOLD @ \$ _____ PER OZ.
 SILVER @ \$ 1.20 PER OZ.
 LEAD @ _____ C.
 COPPER @ _____ C.

CHARGES _____

W. R. Maxwell
 ASSAYER

Established 1916

ASSAY CERTIFICATE

Hand
Sample Serial 34912-18

UNION ASSAY OFFICE, INC.

Mine U. S. 520

M. S. HANAUER, Pres.
J. V. SADLER, V.-Pres. & Treas.
A. C. SELBY, Secretary

Silicious

Telephone Wasatch 1199

Salt Lake City, Utah

RESULTS PER TON OF 2000 POUNDS

July 8, 1936

W.R. Maxwell
J. V. Sadler
Miller

47.92
47.92

NO.	CLASS	GOLD Oz. per Ton	VALUE GOLD	SILVER Oza. per Ton	LEAD Per Cent	COPPER Per Cent	INSOL Per Cent	ZINC Per Cent	SULPHUR Per Cent	IRON Per Cent	LIME Per Cent	
Scorpion Dump	✓	0.040	1.40	29.6	22.80	5.58						24.70
Falcon 1	✓	0.020	.70	26.0	20.02	5.56						20.72
2		0.020	.70	3.7	2.84							3.84
2 A	✓	0.060	2.10	106.5	82.00	9.69						84.00
3		0.010	.35	10.9	8.39							8.39
4	✓	0.040	1.40	53.9	41.50	7.07						42.90
5		0.015	.52	9.2	7.08							7.08

Remarks

Charges \$

7) 192.00
27.94
Miller

WESTERN ASSAYERS

Engineers, Metallurgists and Chemists

224 South Spring St.
Los Angeles, Calif.

NORMAN W. PARLEE, Mining Engineer

PHONE MUTUAL 2906

Special Low Rates to Prospectors

ASSAY CERTIFICATE

Los Angeles, Calif., July 8 1936

We hereby Certify that the samples described below, received from

R. T. Wyllie, 3442 Garnet St. L. A.

assay as follows:

Owner's Mark and Sample	GOLD		SILVER		TOTAL VALUE PER TON	PERCENTAGE OF		
	OZS. PER TON	VALUE PER TON	OZS. PER TON	VALUE PER TON		COPPER	LEAD	ZINC
1280 #1 Falcon	.05	1.75	22.00	16.95	18.70			
1281 #2	.05	1.75	4.76	3.65	5.40			
1282 #2A	.11	3.85	101.72	78.30	82.15			
1283 #3	.04	1.40	9.50	7.30	8.70			
1284 #4	.06	2.10	44.86	34.55	36.65			
1285 #5	.03	1.05	5.96	4.60	5.65			
1286 Scorpion Dump	.07	2.45	35.90	27.65	30.10			

GOLD @ \$33 PER OZ.

LEAD @ \$ C.

SILVER @ \$77 PER OZ.

COPPER @ \$ C.

CHARGES 5.25 Paid

Norman W. Parlee
ASSAYER

Our dependable assays will bring you back — We check, double check and guarantee our work.

WESTERN ASSAYERS

Engineers, Metallurgists and Chemists

224 South Spring St.

Los Angeles, Calif.

NORMAN W. PARLEE, Mining Engineer

PHONE MUTUAL 2908

Special Low Rates to Prospectors

ASSAY CERTIFICATE

Los Angeles, Calif. July 31 1936

We hereby Certify that the samples described below, received from

B. T. Wyllie, 3442 Garnet St., L. A.

assay as follows:

Owner's Mark and Sample	GOLD		SILVER		TOTAL VALUE PER TON	PERCENTAGE OF		
	OZS. PER TON	VALUE PER TON	OZS. PER TON	VALUE PER TON		COPPER	LEAD	ZINC
1397 2A Falcon Stope ore	06	2.10	69.88	53.80	55.90			
1398 2A porphyry	01	.35	3.24	2.50	2.85			
1399 Scorpion shaft	06	2.10	12.60	9.70	11.80			
1400 Falcon dumps	.04	1.40	2.36	1.80	3.20			
1401 Royal ore	01	.70	.68	.50	1.20			

GOLD @ \$ 35 PER OZ.

LEAD @ \$ _____ C.

SILVER @ \$ 77 PER OZ.

COPPER @ \$ _____ C.

CHARGES 3.75 Paid

Norman W. Parlee
ASSAYER

Our dependable assays will bring you back — We check, double check and guarantee our work.

ASSAY CERTIFICATE

Hand Sample Serial 90368-73

UNION ASSAY OFFICE, INC.

U. S. 18

N. J. Wylie + W. R. Maxwell
Lucas Ave

M. S. HANAUER, Pres.
J. V. SADLER, V. Pres. & Treas.
A. C. SELBY, Secretary

Telephone Wasatch 1188
Salt Lake City, Utah

Silicious

RESULTS PER TON OF 2000 POUNDS

Sept. 10, 1936

NO.	CLASS	GOLD Oz. per Ton	VALUE GOLD	SILVER Oz. per Ton	LEAD Per Cent	COPPER Per Cent	INSOL Per Cent	ZINC Per Cent	SULPHUR Per Cent	IRON Per Cent	LIMIT Per Cent
1		Trace		2.5							
2		0.015		36.0							
3		0.015		19.3							
4		0.040		20.6							
5		0.010		12.8							
Prospect											
1		None		None							

Taken in 65 ft level broken ore except #1 sample which is from ledge in shaft station on east side

10 - 7017

Remarks _____
Charges \$ _____

[Signature]

UNITED STATES SMELTING REFINING AND MINING COMPANY
NEWHOUSE BUILDING
SALT LAKE CITY, UTAH
September 11, 1956

Mr. R. T. Wylie & W. R. Maxwell,
Tuscarora, Nevada.

Gentlemen:

The enclosed certificate shows results obtained on the samples you recently sent in.

Ore similar to sample No. 2 would be worth \$21.13 per ton f.o.b. the smelter.

Sample No. 3, \$8.92; sample No. 4, \$11.14; and sample No. 5, \$4.16 per ton f.o.b. Midvale, Utah.

Sample No. 1 and the sample marked "Prospect" do not contain sufficient value to justify shipment.

Product should be billed to U. S. Smelting Refining and Mining Company, Midvale, Utah and bills of lading sent to our Salt Lake City Office.

Very truly yours,

UNITED STATES SMELTING REFINING AND MINING CO.,

By W. H. Bardley
W. H. Bardley
Manager Midvale Plant

21.13
8.92
11.14
4.16
4) 47.35 + 11.87

36
72
18
252
277

5
460
9.65

WHE:CS
Enc.
cc: Mr. Egleston

27.72
9.65
18.107

UNITED STATES SMELTING REFINING AND MINING COMPANY

Provisional Settlement NINTH FLOOR NEWHOUSE BUILDING
4714-A

Salt Lake City, Utah, Sept. 10, 1938

Pay FIRST NATIONAL BANK OF NEVADA, ELKO, NEVADA, for account of: Falcon Mine
Shippers: W.R. Maxwell and R.T. Wyllie SP: Redhouse, Nevada

Ore Crude Lot No. 1 Gold License No.
Sampled by Midvale Received 9/3/38 Sampled 9/7/38 Assayed 9/8/38
Metal Quotations—Gold 34.9125 Silver 64.75 Copper, N. Y. Lead, N. Y. Zinc

ASSAYS	GOLD OZS. PER TON	SILVER OZS. PER TON	PER CENT COPPER WET	PER CENT LEAD	PER CENT INSOLUBLE	PER CENT IRON	PER CENT ZINC	PER CENT SULPHUR	PER CENT LIME	PER CENT
U. S. S. Co.										
Umpire										
Settlement Assay	.055	81.3			93.6	1.7		.4		

CAR NOS.	WET WEIGHT	METAL VALUE		WORKING CHARGE	
WP: 4266		Gold 100% @ 31.8185	1 75	Treatment Base 30% Lead	
		Silver 100% Less 1/2 oz.	51 81	Credit Acc't Over 30% Pb.	
		Copper		Debit Acc't Under 30% Pb.	
		Lead		Insoluble	
		Zinc		Zinc Charge, excess over 6%	
		Total Metal Value	53 56	Sulphur Charge, excess over 2%	
		Less 5 % of value of silver	2 59	Arsenic Charge, excess over 2%	
Total Wet Weight					
Sacks				Total Debit	
Net Weight	23940	Gross Value	50 97	Iron Credit	
Less H ₂ O 1.2 %	288	Less Working Charge	7 30	Net Working Charge	

Dry Weight, lbs. 23652 Payment for 11.826 tons @ 43 67 per ton 516.44
Freight advanced @ 7.15 per ton 20 ton min. 143.00 143.00

Handling Charge Acct. Less Than 10 Tons	
Assay Charges	
Sampling Charges	
Hauling Charges	
Checked by	Amount Withheld Pending Receipt of Silver Affidavit 373.44
Approved by	Net Payment 194.00
	179.58

STANDARD CODES

Cable Address: "ACCURACY"

John Fermin Laboratory

771 San Julian Street, Los Angeles, Calif.

TELEPHONE VANDIKE 6232

U.S.A.

ORE TREATMENT TESTS

Certificate of Assay giving results per ton of 2,000 pounds.

Made for Mr. R. T. WYLLIE,

Date July 2nd, 1940.

OWNER'S MARK	GOLD OZ.	VALUE \$	SILVER OZ.	VALUE \$	OWNER'S MARK	TOTAL \$
	.06	2.10	14.0	9.94		12.04
<i>Sample taken from ledge - 6-20-40</i>						
<i>Value = 6-20-40</i>						
<i>W. J. Fermin</i>						

I DO NOT GUARANTEE SATISFACTION... I GUARANTEE ACCURACY

Pulps under \$10 per ton may be checked by other assayers in good standing with U. S. Bureau of Mines. If it varies over .02 ozs. gold I pay assays. If over .05 ozs. I pay \$5. Higher grades in proportion.

\$11.60

QUOTATIONS USED AS BASIS OF CALCULATION

Gold	\$35.00
SILVER	91
COPPER	
LEAD	

OZ. LB. LB.

John Fermin

ALL VALID CERTIFICATES BEAR THIS SEAL

(OVER)

1142 HOWARD STREET • SAN FRANCISCO 3, CALIFORNIA • UNDERHILL 3-8575

REPORT OF ASSAY

Submitted by

Mr. R. J. ^TWyllie
701 Redwood Highway, South
Crescent City, California

Date October 26, 1961

Sample of Ore

LABORATORY No.	MARK	GOLD, PER TON OF 2,000 LBS.		SILVER, PER TON OF 2,000 LBS.		PERCENTAGES
		TROY OUNCES VALUE AT \$38.00 OZ.		TROY OUNCES VALUE AT \$0.90 OZ.		
6807	Falcon			211.20	217.08	
6808	Scorpion			2.10	2.16	
<p><i>This was taken at random from sack. I suspect the Scorpion is not right as sending more samples than for assay =</i></p>						

METALLURGICAL LABORATORIES

Original Signature of

MARTIN P. QUIST

By _____

PHONE MADISON 2-0328

ASSAY CERTIFICATE

THE EISENHAUER LABORATORIES
316-322 South San Pedro Street
Los Angeles 13, California

Los Angeles, Calif. Sept. 5/62 19

I hereby Certify that the samples described below, received from
W. R. Maxwell assay as follows:

Owner's Mark and Sample	GOLD		SILVER		PERCENTAGE OF			
	OZS. PER TON	VALUE PER TON	OZS. PER TON	VALUE PER TON	TOTAL VALUE PER TON	COPPER	LEAD	ZINC
Cross-cut-65' level, 30' from shaft-7' vein			14.12	\$ 15.95	\$ 15.95			

W. R. Maxwell
ASSAYER

GOLD @ \$35 PER OZ.
SILVER @ \$1.13 PER OZ.
LEAD @ _____ C.
COPPER @ _____ C.
CHARGES \$ 2.50

Established 1916

1142 HOWARD STREET • SAN FRANCISCO, CALIFORNIA
 UNDERHILL 3-8575

REPORT OF ASSAY

Submitted by **Falcon Mining Company**
 c/o Mr. Robert L. Wyllie
 68 Aztec
 San Francisco, California

Date **September 29, 1964**

Sample of **Ore - Primo**

LABORATORY NO. **2340**

MARK	GOLD, PER TON OF 2,000 LBS.		SILVER, PER TON OF 2,000 LBS.		%	%	%
	TROY OUNCES	VALUE AT \$35.00 OZ.	TROY OUNCES	VALUE			
So. Wall and Ceiling 16' Vein	0.02	0.70	2.57	3.31			
No. Wall 15' Vein	0.01	0.35	0.86	1.10			
No. So. Ceiling	0.01	0.35	0.04	0.05			
No. So. Ceiling 4' Center Ledge	0.01	0.35	0.02	0.02			

METALLURGICAL LABORATORIES INC.

By *[Signature]*

METALLURGICAL LABORATORIES

CHEMISTS • ASSAYERS • SPECTROGRAPHERS

1142 HOWARD STREET • SAN FRANCISCO 3, CALIFORNIA
UNDERHILL 3-8575

3872

Falcon Mining Company
c/o Mr. Robert L. Wyllie
68 Aztec
San Francisco, California

September 29, 1964

P. O. NO.

STATEMENT .

LAB. NO.	SAMPLE MARK		
2340	Ore - Primo	4 Gold Assays	\$12.00
		4 Silver Assays	<u>8.00</u>
			\$20.00

ANALYSES OF METAL ORES AND MINERALS

METALLURGICAL LABORATORIES

CHEMISTS • ASSAYERS • SPECTROGRAPHERS

1142 HOWARD STREET • SAN FRANCISCO 3, CALIFORNIA • UNDERHILL 3-8575

Mr. R. J. Wyllie
Falcon Mines
68 Aztec
San Francisco 10, California

January 16, 1963

P.O. NO.

STATEMENT

LAB. NO.	SAMPLE MARK		
8460	Small Sample	1 Gold Assay	\$3.00
		1 Silver Assay	<u>2.00</u>
			\$5.00

ANALYSES OF METAL ORES AND MINERALS

1142 HOWARD STREET • SAN FRANCISCO 3, CALIFORNIA • UNDERHILL 3-8575

REPORT OF ASSAY

Submitted by Mr. R. J. Wyllie
 Falcon Mines
 68 Aztec
 San Francisco 10, California

Date January 16, 1963

Sample of Mineral

LABORATORY No.	MARK	GOLD, PER TON OF 2,000 LBS. TROY OUNCES VALUE AT \$35.00 OZ.		SILVER, PER TON OF 2,000 LBS. TROY OUNCES VALUE AT \$1.00 OZ.	PERCENTAGES
8460	Small Sample	0.005	0.17	Trace	

METALLURGICAL LABORATORIES

By *[Signature]*

THE EISENHAUER LABORATORIES
 316-322 South San Pedro Street
 Los Angeles 13, California

ASSAY CERTIFICATE

PHONE MADISON 2-0320

Los Angeles, Calif. Feb. 27/63 19

I hereby Certify that the samples described below, received from
W. R. Maxwell assay as follows:

Owner's Mark and Sample	GOLD		SILVER		TOTAL VALUE PER TON	PERCENTAGE OF		
	OZS. PER TON	VALUE PER TON	OZS. PER TON	VALUE PER TON		COPPER	LEAD	ZINC
Taken from stope of 65 ft. entrance of Falcon Mine			6395.1	\$7674.12				

GOLD @ \$ _____ PER OZ.
 SILVER @ \$ 1.20 PER OZ.

LEAD @ _____ C.
 COPPER @ _____ C.

CHARGES _____

(5-21-68 - 2.49% Ag = 15,955.52)

Established 1916

[Signature]
 ADJUTANT

THE EISENHAUER LABORATORIES
 316-322 South San Pedro Street
 Los Angeles 13, California

ASSAY CERTIFICATE

PHONE MADISON 2-9328

Los Angeles, Calif. Oct. 28/63 19

I hereby Certify that the samples described below, received from

W. R. Maxwell

assay as follows:

Owner's Mark and Sample	GOLD		SILVER		TOTAL VALUE PER TON	PERCENTAGE OF		
	OZS. PER TON	VALUE PER TON	OZS. PER TON	VALUE PER TON		COPPER	LEAD	ZINC
Found on surface- approx. 200' below Falcon dump <i>High grade Lead</i>			757.40	\$ 977.05	\$977.05			

GOLD @ \$ PER OZ.

SILVER @ \$ 17.29 PER OZ.

LEAD @ C.

COPPER @ C.

CHARGES \$ 2.50

5-21-68 @ 2.49% = 1889.74

W. R. Maxwell
 ANALYST

WESTERN ASSAYERS

Engineers, Metallurgists and Chemists
 224 South Spring Street
 Los Angeles, Calif.
 NORMAN W. PARKER, Mining Engineer

ASSAY CERTIFICATE

Assay # 1

Los Angeles, Calif., Sept. 12, 1940

BUS. MUTUAL 2906
 REG. WALNUT 2872

We hereby certify that the samples described below, received from
W. R. Maxwell, 45 City Hall, L. A.

ASSAY as follows:

Owner's Mark and Sample	GOLD		SILVER		TOTAL VALUE PER TON	PERCENTAGE OF	
	OZS. PER TON	VALUE PER TON	OZS. PER TON	VALUE PER TON		COPPER	LEAD
7783, Concentrate, Piece	6.32	221.20	1.87	1.31	222.51		
<p><i>Concentrate</i> <i>1973 - Gold</i> <i>1973 - Silver @ 2.67</i> <i>Parish</i> <i>W. R. Maxwell</i> <i>54.95 =</i> <i>346.97</i> <i>11.99</i> <i>358.96</i></p>							

GOLD @ 35 PER OZ. LEAD @ _____ CENTS
 SILVER @ 71 PER OZ. COPPER @ _____ CENTS
 CHARGE 254 Paid Kornacker
 ASSAYER

Our dependable assays will bring you back — We check, double check and guarantee our work.